Portland State University

PDXScholar

Dissertations and Theses

Dissertations and Theses

1979

Pictoforms

Ellen Birnbaum

Portland State University

Follow this and additional works at: https://pdxscholar.library.pdx.edu/open_access_etds

Part of the [Art and Design Commons](#), and the [Art Practice Commons](#)

Let us know how access to this document benefits you.

Recommended Citation

Birnbaum, Ellen, "Pictoforms" (1979). *Dissertations and Theses*. Paper 3490.

<https://doi.org/10.15760/etd.5374>

This Thesis is brought to you for free and open access. It has been accepted for inclusion in Dissertations and Theses by an authorized administrator of PDXScholar. Please contact us if we can make this document more accessible: pdxscholar@pdx.edu.

To the office of graduate studies in
research :

The members of the committee approve the
thesis project of Ellen Birnbaum
Presented October 20, 1979

[REDACTED]
Andrea Joseph, chairman

[REDACTED]
Mary Constans

[REDACTED]
Ray Grimm

[REDACTED]
James Hibbard

[REDACTED]
Robert Kasal

[REDACTED]
Michihiro Kosuge

Approved :

[REDACTED]
Leonard Kimbrell, head, department of
art and architecture

Pictoforms

by Ellen Birnbaum

*A thesis project report submitted in partial
fulfillment of the requirements for the degree
Master of Fine Arts in Art*

*Portland State University
1980*

Petroglyphs are composed of a large alphabet of symbols. Many nomadic tribes used combinations of pinwheels, zigzags, ladders, crosses, and lines to communicate ideas. These abstract symbols are narrative images which express their meanings pictorially. For example a circle "O" may mean an enclosure, nothing or empty, a moon or a planet. The exact interpretation of symbols is dependent on two variables. (1) The symbol may have a predetermined meaning prescribed by set rules within a cultural environment. Numerous historic picture languages use many of the same symbols to signify very different meanings. (2) The symbol may have a meaning dependent upon its relationship to other symbolic elements, by its placement on the rock and by juxtapositions. A circle above a line "O" could mean a moon over the land or a circle around a solid dot "◎" might signify an enclosure around an object.

I have coined the word pictoform for my sculpture from the root words picto and form, specifically meaning a mental image or idea in combination with a physical structure or shape. My pictoforms are sculptural structures which evolved from the hieroglyphic petroglyphs and pictographs that I have studied in Northwestern United States. The carved and painted picture writing on the rocks in this area is unique for its communicative intent to indicate specific land forms along various trails. My research began with the investigation of the iconographic content of these images in order to develop three dimensional markers of my own.

I have chosen to work with the idea of interpreting a symbol through juxtaposition with other symbols

as an expression of meaning. This opens each sculptural image to a variety of interpretations dependent on the viewer's personal interaction with the form. The interpretation of the pictoforms is based on two following independent and yet integral principles.

(1) The line and triangle elements are reiterated throughout the form, both in the negative and positive space. This creates a poetic rhythm which carries the eye throughout and around the structure.

(2) The joining of the clay parts by tying, lashing and pinning is of visual and functional importance to each form. Untanned rawhide straps have been used because the color, texture and structural rigidity are in keeping with the feeling of the clay. The bindings were simply overlapped and ends tucked in to act as focal points of connection and stress.

At first I used many of the same symbolic forms found in petroglyphs. Discs, rakes, ladders, and arches were foreign to my immediate experience and the resulting work looked contrived, the intent unclear. I then limited my forms to two symbols that are derived from natural forms easily found in the outdoors, the stick and the rock. These suited my purpose well as shapes which are natural components for combining visually and for structurally binding together. I developed them into the line and triangle.

The constructed clay line is a large rolled rod. I began rolling the clay with my hands, and then

completed the action by rolling it with large flat boards to obtain a smooth surface. The triangles were shaped by pounding and rolling the solid clay. Then, many were cut open with a wire, hollowed out and reassembled. These techniques were a direct result of my choice to have the forms appear unmanipulated and to retain a distinctive clay-like quality.

I decided these shapes needed natural colored and textured surfaces. Earthy colors are easily obtained with all the mineral colorants used in ceramic chemistry, but how to apply the color so that it appears to grow from within the form and not seem applied was a problem. The solution was the application of sulfides (soluble salts) to the clay. These should be dissolved in water and sprayed on, wedged into, or rolled and pounded into the surfaces. The salts dissolve into the clay and re-surface during the firing process. Clay rolled over the sulfide particles takes on a pitted surface texture. Sulfides are responsive to the spontaneity of the work process from start to finish. Coloring results vary with each firing and also with the color of the clay body. I chose brown stoneware, white stoneware, and porcelain clays, determining the color desired in the final form. Additional clay surfaces were obtained by rolling the clay over sawdust, ceramic colorants (such as burnt umber, yellow ochre, black nickel oxide, and green stain) and various colored fire clays (troy fine clay, Scholls earthenware, kaolin, and bentonite). This process dries the surface and creates beautifully intricate cracking patterns on the surface as the clay is stretched. Some forms were saggar fired in order to achieve a smokey and fire scarred effect. My method of saggar firing produces subtle flashes of browns and oranges on

stoneware clay and smoky grays, oranges and metallic blacks on porcelain. Unlike most protective firing chambers which shield the clay from spontaneous flash effects in the kiln, saggars were used to produce fire variables in the kiln and keep them on the pieces. To make saggars I built brick walls around the pieces in the kiln with a small opening at two opposite ends for the flames to pass through. Wood chips were packed around the pieces and then the top of the saggars was closed off with the kiln shelves.

The combined effect of the natural surfaces and the content creates in each sculptural form an expressive entity. One form has two triangles which are bound so that they become the structural support for the span of an arch. This form suggests to me that there is a bridge which though safe for crossing may not support heavy loads. Caution should be taken when crossing. Another sculpture sustains a triangle high in the crossing apex of two towering thin lines. This form might indicate hazards overhead. These two examples demonstrate how the joining of simple elements pictorially conveys a fundamental idea which the viewer might expand upon in relation to his own experience. I feel the sculptures do not need a natural environment to be understood. Isolated against unobtrusive white walls of a gallery and with simple spot lighting, they gain a monumentality and alluring presence which promotes contemplation.

The large size of the forms in relation to the human form intimates a participation with the clay sculpture. The linear feeling of the forms creates an airiness which reaches out into the surrounding space. These qualities give the pictoforms a fragile nature and an impression

SULFIDES

A technical study of metallic color
sulfides to create interesting clay surfaces

Metallic Sulfides on Clay

The association with the outdoors and directness of the sculptural forms in this study made me seek a non glazed surface rich in color and texture, having a life from within the clay itself rather than an obviously applied colorant or color dependent on spontaneous firing methods such as raku, salt, or saggar fires. Observation of accumulated surface residues in high alkaline earthenware clays during the drying process inspired me to examine the effects of metallic salts in a clay body. These are salts of sulfurous acid called sulfides, and salts of hydrochloric acid (chlorides) bonded with other elements. They are water soluble. Applied to clay they penetrate with the water in the clay body and resurface as crystals during the drying process of the greenware creating intricate patterns of color and visual texture which seems to be a part of the clay. The effects of the sulfides must be varied according to the color of the clay body, temperature and atmosphere of the firing, method of application to the clay, intensity of the solution, and the rate of drying the greenware.

Technical Data

The list of sulfides and their recommended quantities for dissolution in 100 c.c. water was obtained in the Scientific Chemical

Index. These are:	copper sulfate	30 grams
	potassium dichromate	60 grams
	cobalt sulfate	10 grams
	iron sulfate	30 grams
	magnesium sulfate (epsom salts)	70 grams
	chromium sulfate	13 grams
	nickel chloride	20 grams
	manganese chloride	25 grams

In addition to the tests done with these formulas, other tests incorporated the saturation of some color solutions which seemed weak and might benefit by intensifying the color. I increased the intensity of cobalt sulfate to 50 grams, nickel chloride was doubled to 40 grams, and manganese to fifty grams. Several sulfide combinations were tested in solution also.

Iron	30 grams + chrome 4 grams
Iron	6 grams + chrome 12 grams
Iron	15 grams + cobalt 12 grams
Manganese	45 grams + chrome 5 grams

Five methods for applying the sulfides to the clay were tested. These will be referred to in the test charts by number.

1. Dipping wet clay into salt solution
2. Dipping dry greenware in solution
3. Dipping bisque ware ($\Delta 08$) in solution
4. Spreading sulfide crystals on a table surface and rolling the clay over them.
5. Wedging sulfides into the clay.

The clay itself determines the fired appearance of the salt color. The first series of tests were done with two stoneware bodies, one of which contains a quantity of red earthenware clay. Results of the two stonewares showed so little difference that further tests were completed with only my favorite stoneware clay, porcelain, and a white stoneware. The clay bodies employed in testing were:

Missouri-Lincoln Stoneware (ML)... a highly plastic clay good for both handling and throwing.

A.P. Green Missouri fire clay	60
Lincoln 60 clay	40
Potash fieldspar	10
OM4 ball clay	5
10% Grog	

BR stoneware ... very smooth, brown clay, especially good for handbuilding with large slab forms and sensitive to detailed surface qualities.

A.P. Green Missouri fire clay	100
OM4 Ball clay	75
Red art	25
Potash fieldspar	10
Grog 10%	

Δ 04 Whiteware

Talc	50
Ball clay	40
Nepheline Syenite	10

Porcelain ... excellent for throwing or handbuilding

Kaolin (EPK and Grolleg)	40
Potash feldspar	30
Flint	20
Pyrophyllite (pyrotrol)	10
Bentonite	3
Om4 Ball Clay	10

White Stoneware... a pale gray clay

M3 77 Clay	100
Ajax 6T Kaolin	60
Custer feldspar	30
OM4 Ball Clay	60
Flint	27
Grog	15

Each table is for a particular sulfide solution. The tables do not give details of every possibility tested. They are a summary of the most interesting results. Results are listed for each clay body, first by division of temperature and firing, and then numbered according to the method of application. Asterisks mark the most successful results obtained. A summary of information unique to each sulfide is listed at the bottom of each table.

Copper 30 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Whiteware	Δ 04	pale brown
Porcelain	Δ 08 Bisque	1 pale green to charcoal
		2,3,4 gray to charcoal
		5 charcoal to black
	Δ 6 oxidation	pale green to metallic pewter
		5 all metallic, no soft color bleeding
	Δ 10 Reduction	* 1,2 soft grey-green, textural spotting
* 3 mauve to gray bleeding		
4 textured green gray with metallic black areas		
5 black		
BR and ML Stoneware		
Δ08 Bisque	2 yellow brown-black spots	
	4 pale brown with black texture	
	5 brown to black, texture evenly gray	
Δ 6 oxidation	1,2,3 green gray	
	4 grayish black mottles with metallic gray areas	
	5 metallic gray	

Copper sulfate crystals are large enough to cause a pitted texture when pressed into the clay, creating a tactile texture as well as an unusually rich visual color texture. This sulfate mottles and spots in the drying process more readily than most sulfides. Results are best on porcelain clay. Too much concentration of the copper produces blacks. Softer colors are best achieved by applications 1 and 2 with slow drying.

Potassium Dichromate 60 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Whiteware	Δ 04	textural spotting, olive green
Porcelain	Δ 08 Bisque	1,2 overall pale green, dark green speckles
		4 textural clay, green
		5 solid green where fast dried, slow drying results in pale green with dark speckles
	Δ 6 oxidation	1,2,3 darker green than low fire
	Δ 10 reduction	1,2 pale gray-green with lusterous brown spotting
		3 lusterous gold-brown color texture
BR and ML Stoneware	Δ 08 Bisque	4,5 self glazes, ugly army green
		1,2,3 pale green
	Δ 6 oxidation	4,5 Green with dark green mottling
		1,2,3 green brown with overall mottling
		4,5 olive green, much texture
	Δ 10 reduction	1,2,3 Dark green-gold and brown overall. Darkest on BR clay
		4,5 BR clay self glazes army green color. ML clay self glazes brown.

Potassium produces fairly uniform results. Dried slowly it forms textural dot patterns. The raw crystals create a delicate tactile pattern in the clay when applied with methods 4 and 5. Method 3 is the most successful.

Cobalt 10 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Whiteware	Δ 04	pale blue with medium blue texture
Porcelain	Δ 08 Bisque	1,2 very pale gray, some medium gray "smoking" effects
	Δ 6	pale blue bleeding into black
	Δ 10	blue bleeding into dark blue
BR and ML clays	Δ 08 Bisque	1,2,3 pale blues or grays
	Δ 6 oxidation	3 pale gray blue

Cobalt 50 gr./100 c.c. water

Results are similar to the lighter solution except that pale blues are bright blue. All colors are more intense.

Cobalt sulfate is a powder crystal which leaves no texture on the clay surface. Colors bleed in smoky patterns between shades of light to dark with mottling or spotting. Δ 08 produces grays where higher temperatures make more intense blues.

Iron 30 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Whiteware	Δ 04	orange rust color with soft mottling
Porcelain	Δ 08 Bisque	1,2 pale orange with rust bleeding
		4 overall rusty color, some whitish soda deposit
		5 dark rust overall with a few black iron spots
	Δ 6 oxidation	results are similar but with darker colors
	Δ 10 reduction	1,2,3 Amber with metallic cordovan rust color
BR and ML clays		4 dark amber
		5 metallic iron overall
		are similar to porcelain results, but without the brilliance due to the darker clay color.

Two kinds of iron sulfates are available for purchase. Ferric sulfate (a yellow powder) and ferrous sulfate both give the same color results. The ferrous iron crystals are small pellets and create a texture when used in methods 4 and 5. I also prefer the ferrous iron because it gives off fewer fumes when exposed to air.

Iron does not fuse well to the clay when fired to temperatures below Δ04. Fast drying creates dark colors and bleeding effects. Slow drying produces softer pale colors and spotting.

Magnesium (Epsom Salts) 70 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Whiteware	Δ 04	no visual results
Porcelain	Δ 08, Δ6	no visual results
	Δ 10 Reduction	causes a flux reaction which makes the clay glassy
BR and ML Clays	Δ 08, Δ6	no visual results
	Δ 10 Reduction	4,5 color of clay changes into subtle smokey patterns. BR clay acquires a yellowish tint bleeding into gray rings and whites. Fast drying creates more overall white and a crust which flakes off. Slow drying creates subtle smokey markings.

Interesting textures are created with epsom salts similar to those of ferrous iron crystals. In drying, flaky crystals grow out of the clay. These may be brushed off or left on during the firing with no difference in final color results.

Nickel Chloride 20 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Porcelain	Δ 6 oxidation	1,2,3 produces greenish browns
		* 4,5 beautiful sea green
	Δ 10 reduction	1,2,3 pale greenish brown
		4,5 pale green surface
BR stoneware - no interesting results except:		
	Δ 6 oxidation	* 5 yellow green moss color
White Stoneware	Δ 6 oxidation	1,2,3 pale tan
		* 4,5 bleeding from moss green to golden browns
	Δ 10 reduction	1,2,3 light tan coloring
		* 4 moss green bleeds into a dark brown

Nickel Chloride 40 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Porcelain	Δ 6 oxidation	1,2,3 produces olive greens
	Δ 10 reduction	1,2,3 produces silvery green gray

All other tests on porcelain and stonewares show no marked variance from the lighter solution.

Nickel chloride must be ground to a powder. The crystals create a tacky wet goo which makes it difficult to work methods 4 and 5.

Nickel tends to spread on the clay surface evenly giving no textural color qualities.

Manganese Chloride 25 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Porcelain	Δ 6-10	May produce pale tan. Results are not consistent.
	Δ 6 oxidation	5 makes a mottled gray brown and dark brown
BR Stoneware	Δ 6 and 10	clay appears brown
	Δ 6 oxidation	4,5 golden brown
	Δ 10 reduction	4,5 dark brown
White Stoneware	Δ 6 oxidation	buff tans result
	Δ 10	pale browns result

Manganese Chloride 50 gr./100 c.c. water

No significant differences result on any of the clays.

Chrome 4 gr. - Iron 30 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
Porcelain	Δ 08	1,2 pale gold brown, 2 is brighter
		4 brown bleeding with green, green stays on surface as a powder which rubs off
	Δ 6 oxidation	1,2 brown bleeding into green. powder rubs off. 2 is darker.
		5 iron shimmers brown with green texture which is partially fluxed.
	Δ 10 reduction	1 pale golden brown
		2 dark metallic gold brown
3 silverish color results		
BR and ML stoneware	Δ 6 oxidation	1,2,3 pale greenish brown bleeding effects
		4 Green texture on dark ground, green texture still does not flux
	Δ 10 reduction	1,2,3 dark browns
		4 Green texture on dark ground, green texture still does not flux

Chrome 12 gr. - Iron 6 gr./100 c.c. water

The results are similar to the above, but less interesting, no greens result and browns are murky and gray.

Cobalt 12 gr. - Iron 15 gr./100 c.c. water

<u>Clay</u>	<u>Temperature</u>	<u>Results</u>
* Whiteware	Δ 04	blue gray bleeding into black
Porcelain	Δ 08	1,2,3 gray bleeding into black
		4 yellowish-blues bleed to dark grays
		5 smokey greys, blues and blacks where dried slowly, black where drying is rapid
	Δ 6 oxidation	1 blue gray bleeds to black
		2,3 dark gray bleeds to black
		4 clay texture, blue gray to black
		5 black
	Δ 10 reduction	same as Δ6
BR and ML stoneware		results are the same as with porcelain

This combination seems to turn solid black if dried quickly.

Slow drying aids soft, subtle bleeding effects.

Glaze with Sulfides

I have also tested clear glazes over stoneware temperature tests.
Listed below are the most interesting results.

Copper: $\Delta 6$ oxidation Light green color

$\Delta 10$ reduction

1,2,3 green to red textural coloring

4,5 dark reds and metallic glassy where the
sulfate is heavily applied

Potassium Dichromate:

$\Delta 6$ oxidation 3 yellow brown

$\Delta 10$ reduction 3 pale green

4,5 grass green-brown color, very ugly

Cobalt Sulfate: intense blue glaze bleeding into black

Iron: Glazes are most successful with iron, producing ambers in
 $\Delta 6$ oxidation. 4,5 application methods produce a salmon
color blending into dark cordovan.

$\Delta 10$ reduction produces an effect similar to temmochu.

Magnesium: Glaze does not adhere to the surface, blisters and
crawling result.

Chrome: Results are the same as the unglazed surface. The gloss
darkens the surface.

Nickel: $\Delta 10$, 5 metallic luster effects appear.

Iron-Cobalt: Glaze darkens the blues. In tests where light
blues bleed into black, the glaze darkens the cobalt
blue color.

Raku

Bisque fired tiles of white stoneware and BR stonewares were first dipped in the solutions before a clear low fire glaze was applied. The unglazed half of each tile was lightly sprayed with the clear glaze to prevent the reduction from making a totally black clay. The second half of each tile was covered with a full coating of clear glaze.

- * Copper: Textural colors of red, green and yellow appear under the lightly sprayed and glazed areas.

Potassium: No effect.

Cobalt: 50 gr. solution - grays and blues, dark blue under full glaze

- * Iron: Salmon color bleeds and mottles with a dark rust.

Magnesium: No effect.

Chrome: golden brown on BR clay, grayish on white stoneware

Nickel: some pale brown smoking

Iron-cobalt: on white stoneware silvery gray patterns

Manganese: No effects.

Chrome Iron: pale yellow on white stoneware, yellow brown bleeding to dark golden color on BR clay

Conclusion

The results of sulfide colors are most influenced by the rate of drying. Fast drying causes overall patterns in dark colors and slow drying forms softer coloring with delicate textural variations often blending from one shade to the next. The only way I can account for this is that no matter how the sulfate is applied, it immediately soaks into the clay, almost disappearing. Rapid drying draws the sulfate out more thoroughly than slow drying which seems to allow the sulfate to settle within the clay. Porcelain is the best clay for allowing the colors to show because it is white and does not camouflage or alter the delicate colors. The fluxing properties of the porcelain in combination with some of the salts produce a metallic sheen. Application of the sulfate to bisqueware by spraying, dipping or painting (method 3) most often produces the brightest colors obtainable with a wet solution. Methods four and five produce rich colors with the addition of surface texture from the dry sulfate crystals. The stronger colorants such as iron, potassium, copper and cobalt sulfates may be brushed on in the manner of water colors with results changing little from the painted image. Spraying with a mouth atomizer works very well if care is taken to apply a thin coating which is almost invisible. Too heavy an application produces murky browns and blacks. Some experiments were done applying a sulfate on a high fired clay and refiring to a low temperature. This achieved the low-fire sulfate colors with the advantage of a strong high-fired clay body. The results of this technique are that the colors obtain a more even coating of color without creating delicate surface patterns. In addition, much

of the color will wash off unless fired to cone 04 or higher.

Care must be taken not to inhale the sulfide vapors. These cause nausea and dizziness. Kept in tight dry containers, the sulfides will keep indefinitely. The longer the solution sits, the stronger it seems to get.

The tests here are but a beginning of many combinations yet to be tried. The color possibilities produced by metallic sulfides vary with every firing and application. Though not always predictable, the salts offer a wide range of surface variety treatments adaptable to many types of firing.